

DESCRIPTION

PP-CF is a two parts, high penetration, fast setting, hybrid polyurea for repairing and re-building damaged concrete. The product is a 1:1 ratio, easy to mix system that is 98 % solids and VOC compliant. The PP-CF can be used to set anchor bolts, repair damaged control joints, fill spalling, and rebuild vertical curbing and steps. Sand or gravel can be added to extend the volume of the material and acts as filler for repairing large spalls, holes and cracks.

WHERE TO USE

- Commercial freezer repairs
- Aircraft hangar floors
- Low temperature equipment
- Maintenance facility floors
- Garage floors
- Industrial shop floors
- Car washes or wash bays
- Forming/ rebuilding stairs and steps
- Leveling and grade matching
- Bridge/ street repairs
- Concrete polishing and other coating applications
- Non-moving control joint fill

ADVANTAGES

- Application temperature between -5 C to 38 C
- Product cures in 10 minutes @ 22 C with excellent adhesion
- Self-leveling and self-priming
- Ready to service in 10 to 20 minutes
- Easy to mix 1:1 ratio by volume
- Highly chemical resistant
- Excellent for industrial floor repairs subject to forklift traffic and harsh conditions

TECHNICAL DATA

PACKAGING	7.57 L (2 US GAL KIT)		
COLOR	PART A BLACK	PART B AMBER	MIX (LIQUID/CURED) BLACK/GREY
SHELF LIFE	12 MONTHS IN ORIGINAL UNOPENED FACTORY SEALED CONTAINERS. STORE IN DRY COOL PLACE BETWEEN 10 AND 32 °C (50 AND 89 °F). KEEP OUT OF DIRECT SUNLIGHT AND AWAY FROM FIRE HAZARDS.		
MIX RATIO, BY VOLUME	A:B = 1:1		
MIX RATIO, BY WEIGHT	A:B = 100:118		
POT LIFE (100 G @ 25°C)	2-3 MINUTES		
CURE TIME (@ 22°C)	10-15 MINUTES		

PROPERTIES @ 23 °C (73 °F) AND 50% R.H.

DENSITY (KG/L)	PART A 0.94	PART B 1.12	MIX 1.11						
DRYING TIMES (RELATIVE HUMIDITY 72F – 50%)	<table border="0"> <tr> <td>HARD DRY</td> <td>5-10 MINUTES</td> </tr> <tr> <td>FOOT TRAFFIC</td> <td>10 MINUTES</td> </tr> <tr> <td>VEHICLE TRAFFIC</td> <td>30 MINUTES</td> </tr> </table>			HARD DRY	5-10 MINUTES	FOOT TRAFFIC	10 MINUTES	VEHICLE TRAFFIC	30 MINUTES
HARD DRY	5-10 MINUTES								
FOOT TRAFFIC	10 MINUTES								
VEHICLE TRAFFIC	30 MINUTES								
TENSILE STRENGTH (PSI), ASTM D638	4500-4800								
ELONGATION (%), ASTM D638	6 - 8%								
BOND STRENGTH (PSI), ASTM D4541	1900-2300								
COMPRESSIVE STRENGTH (PSI) LIQUID, ASTM C109	5600								
HARDNESS (SHORE D), ASTM D2240	68-72								
VISCOSITY (CPS) @ 25°C	PART A 15-30	PART B 15-30	MIX 15-30						

SURFACE PREPARATION

The surface must be cleaned before the application of the product. BLASTRAC, sand blasting, diamond grinder w/30 grit or coarse, or water blasting is highly recommended to remove surface contaminants. Any oils and fats must be removed prior to product application. The surface must be primed and allowed to dry before the application of the product. Compression resistance of concrete must be at least 25 MPa (3625 lbs./inch²) after 28 days and traction resistance must be at least 1,5 MPa (218 lbs./inch²).

MIXING

Mix each component separately. Pour component B into component A using the proper mixing ratio. Mix together both components for not more than 30 seconds. Only prepare quantity that may be applied during pot life.

APPLICATION

Apply and pour the mixed product on the prepared surface

CLEANING

Clean all application equipment with a specified cleaner. Once the material hardens it can only be removed mechanically. If the product splatters, wash thoroughly with hot soapy water.

RESTRICTIONS

- Minimum/Maximum temperature of substrate: 10 °C / 30 °C (50°F / 86 °F).
- Maximum relative humidity during application and curing: 85 %.
- Substrate temperature must be 3 °C (5.5 °F) above dew point measured.
- Humidity content of substrate must be < 4 % when coating is applied.
- Avoid exterior use on substrates at ground level

HEALTH AND SAFETY

In case of skin contact, wash with water and soap. In case of eye contact, immediately rinse with water for at least 15 minutes. Consult with a doctor. For respiratory problems, transport victim to fresh air. Remove contaminated clothes and clean before reuse. For more information, consult the material safety data sheet.

Components A and B contain toxic ingredients. Prolonged contact of this product with the skin is susceptible to provoke an irritation. Avoid eye contact. Contact with may cause serious burns. Avoid breathing vapors release from this product. This product is a strong sensitizer. Wear safety glasses and chemical resistant gloves. A breathing apparatus filtering organic vapors approved by the NIOSH/MSHA is recommended. Predict suitable ventilation.

Consult the material safety data sheet for further information.

IMPORTANT NOTICE

All statements, recommendations and technical information contained in this document are accurate to the best knowledge of PurEpoxy. The data relates only to the specific material designated herein. It may not be valid if used in combination with any other materials. It is the users' responsibility to verify suitability of this information for their own particular use, and to test this product before use. PurEpoxy assumes no legal responsibility for use upon these data. PurEpoxy assumes no legal responsibility for any direct, indirect, consequential, economic, or any other damage except to replace the product or refund the purchase price as set out in the purchase agreement.